

EP 65115 (100 %) PRODUCT CODE – EP 65115







TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY		1.15 ±0.05	ASTM D297	1.15±0.05
HARDNESS	ISO 48-4	65 ± 5 Sh A	ASTM D2240	65 ± 5 Sh A
TENSILE STRENGTH (min)	ISO 37	1991 PSI	ASTM D412	140 kg/cm 2
ELONGATION AT BREAK (min)	ISO 37	400%	ASTM D412	400 %
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	30 %	ASTM D395 METHOD B	30 %
TEAR RESISTANCE (Angular) min	ISO 34-1	224 Lbs/Inch	ASTM D624	40 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
HARDNESS (Pts)		+ 2 (Max)		+ 2 (Max)
TENSILE STRENGTH (%)		+ 8		+ 8
ELONGATION AT BREAK (%)		+15		+15
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE		EXCELLENT	ASTM D 1149	EXCELLENT
DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 130° C		-30 ° to + 130° C
COLOR		BLACK		BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*















