

## EPDM 60130 FG PRODUCT CODE – EPDM 60130 FG



## **TECHNICAL SPECIFICATIONS**

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
HARDNESS	ISO 48-4	60 ± 5 Sh A	ASTM D2240	60 ± 5 Sh A
TENSILE STRENGTH ( min )	ISO 37	711 PSI	ASTM D412	50 kg/cm 2
ELONGATION AT BREAK ( min )	ISO 37	250 %	ASTM D412	250 %
TEAR RESISTANCE (Angular) min	ISO 34-1	101 Lbs/Inch	ASTM D624	18 Kg/cm
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	40 %	ASTM D395 METHOD B	40 %
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	MT _
HARDNESS (Pts)		+5 (max)		+5 (max)
TENSILE STRENGTH (%)		+ 10 /- 10		+ 10 /- 10
ELONGATION AT BREAK (%)		+ 10 / -10		+ 10 / -10
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE		EXCELLENT		EXCELLENT
DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
OILS		EXCELLENT		EXCELLENT
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-25° to + 120° C		-25° to + 120° C
COLOR		OFF WHITE		OFF WHITE

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*





















