

SILICON 60120 FG product code – SI 60120 FG







TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		FPS UNITS
SPECIFIC GRAVITY		1.20 ± 0.05	ASTM D297	1.20 ± 0.05
HARDNESS	ISO 48-4	60 ± 5 Sh A	ASTM D2240	60 ± 5 Sh A
TENSILE STRENGTH (min)	ISO 37	853 PSI	ASTM D412	60 kg/cm 2
ELONGATION AT BREAK (min)	ISO 37	250 %	ASTM D412	250 %
TEAR RESISTANCE (Angular) min	ISO 34-1	112 Lbs/Inch	ASTM D624	20 Kg/cm
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	45 %	ASTM D395 METHOD B	45 %
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	ТМ
HARDNESS (Pts)		+3 (max)		+3 (max)
TENSILE STRENGTH (%)		+5 / 5		+5 / -5
ELONGATION AT BREAK (%)		+5 / -5		+5 / - 5
VOLU <mark>ME</mark> SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE		EXCELLENT		EXCELLENT
DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
OILS		NOT RECOMMENDED		NOT RECOMMENDED
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-90° to + 220° C		-90° to + 220° C
COLOR		WHITE / BRICK RED / BLUE		WHITE / BRICK RED / BLUE

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*





DSIR









