


**NR-SBR 40110**
**PRODUCT CODE –NR-SBR 40110**

**TECHNICAL SPECIFICATIONS**

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	-	1.10 ± 0.05	ASTM D297	1.10 ± 0.05
HARDNESS	ISO 48-4	40 ± 5 Sh A	ASTM D2240	40 ± 5 Sh A
TENSILE STRENGTH ( min )	ISO 37	2347 PSI	ASTM D412	165 kg/cm <sup>2</sup>
ELONGATION AT BREAK ( min )	ISO 37	600%	ASTM D412	600 %
COMPRESSION SET (70°C/22 hrs/25% compression) (max)	ISO 815-1	30 %	ASTM D395 METHOD B	30 %
TEAR RESISTANCE ( Angular ) min	ISO 34-1	224 Lbs/Inch	ASTM D624	40 Kg/cm
ABRASION RESISTANCE ( max )	ISO 4649	120 mm <sup>3</sup> (10 N)	ASTM D5963	120 mm <sup>3</sup> (10N)
RESILIENCE		60%		60%
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C )			ASTM D573	
--- HARDNESS (Pts)		+5 (Max)		+5 (Max)
--- TENSILE STRENGTH (%)		+10/-15		+10 / -15
--- ELONGATION AT BREAK (%)		+10 / -25		+10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 70° C		-40 ° to + 70° C
COLOR		PINK/ORANGE		PINK/ORANGE

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement. \*