

AB 65125 BLACK PRODUCT CODE – NR 65125



TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		FPS UNITS
SPECIFIC GRAVITY		1.25 ± 0.05	ASTM D297	1.25 ± 0.05
HARDNESS	ISO 48-4	65 ± 5 Sh A	ASTM D2240	65 ± 5 Sh A
TENSILE STRENGTH (min)	ISO 37	1422 PSI	ASTM D412	100 Kg/cm 2
ELONGATION AT BREAK (min)	ISO 37	350 %	ASTM D412	350 %
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	35 %	ASTM D395 METHOD B	35 %
TEAR RESISTANCE (Angular) min	ISO 34-1	140 Lbs/Inch	ASTM D624	25 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
HARDNESS (Pts)		+ 5 (max)		+ 5 (max)
TENSILE STRENGTH (%)		+10 /-25		+10 /-25
ELONGATION AT BREAK (%)		+10 /-25		+10 /-25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		N <mark>OT</mark> RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE		FAIR	ASTM D 1149	FAIR
DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
OILS		NOT RECOMMENDED		NOT RECOMMENDED
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-25° to +70° C		-25° to +70° C
COLOR		BLACK		BLACK
AT , A11 ' , 1 C '11 , ,' 1 A				

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*























